

DEFENDER II™



DESCRIPTION

- DEFENDER II™ Microporous Shoe Covers
- Lighter, Cooler Version of the Original
- Serged Seams
- Latex Free Elastic
- Safe for Food Contact

Ideal for: Agriculture, Mold Remediation, Asbestos & Lead Abatement, Pharmaceuticals, Clinics, Hospitals, Food Processing & Pesticides. Defender II Shoe Covers provide protection in work environments where hazardous and non-hazardous liquid and dry particulate contaminants may be present.



DESCRIPTION:		CERTIFICATIONS & RATINGS:						
DEFENDER II™, Microporous Shoe Covers, Latex Free Elastic, Serged Seams See attached Physical Properties		Made with FDA Approved Materials for food contact Applications. (U.S. Code of Federal Regulations, 21CFR, Parts 170-199)						
APPLICATIONS:		ORDERING:	BARCODES:					
AGRICULTURE PAINTING FOOD PROCESSING LABORATORIES	Unit of Sale: One Case Packaging: 50 EA/Polybag Case Pack: 200 EA/Case COO: China Available Sizes: L	<table border="1"> <thead> <tr> <th>ITEM</th> <th>ITEM UPC</th> <th>CASE UPC</th> </tr> </thead> <tbody> <tr> <td>MPSCCL</td> <td>796326100806</td> <td>-</td> </tr> </tbody> </table>	ITEM	ITEM UPC	CASE UPC	MPSCCL	796326100806	-
ITEM	ITEM UPC	CASE UPC						
MPSCCL	796326100806	-						
CARE:		Case Weight (lbs) 4 lbs.						
Dispose after each use.								

PHYSICAL PROPERTIES

DEFENDER II™ Shoe Covers

TEST DATA

PHYSICAL PROPERTY	TEST METHODS	UNITS	RESULTS
Fabric Weight	IST130.1	gsm	49.86/1.47 oz
MD Tensile (Grab)	IST110.1	lbs/in	25.5
CD Tensile (Grab)	IST110.1	lbs/in	16.5
MD Elongation	IST110.1	%	67.8
CD Elongation	IST110.1	%	76.5
MD Tear Strength (Trapezoid)	IST100.2	lbs/in	6.5
CD Tear Strength (Trapezoid)	IST100.2	lbs/in	10.3
Bursting Strength (Mullen Burst)	IST 30.1	psi	30.5
Hydrostatic Head	IST 80.6-01 (Testex)	cm	191.3
Static Decay(MD) (50%RH)+	IST 40.2	sec	Pass
Resistance to Blood Penetration	ASTM 1670	Procedure B	Pass

*These physical properties represent typical values of the non-woven fabric. These values should not be considered as a specification or certificate of material and/or specification value. Testing was performed on base material.

Corporate Headquarters:

4025 Viscount Avenue
Memphis, TN 38118
Phone 800.458.8763
Fax 901.458.3343

CORE SAFETY PROTECTION
www.cordovasafety.com

West Coast Office:

433 Cheryl Lane (Dock Door 14)
City of Industry, CA 91789
Phone 909.590.2679
Fax 909.590.3130

