

DEFENDER™



DESCRIPTION

- DEFENDER™ Microporous Coveralls
- Serged Seams
- Zipper Front & Collar
- Elastic Wrists & Ankles
- Attached Hood
- Safe for Food Contact

Ideal for: Agriculture, Mold Remediation, Asbestos & Lead Abatement, Pharmaceuticals, Clinics, Hospitals, Food Processing & Pesticides. Defender CPH Coveralls provide protection in work environments where hazardous and non-hazardous liquid and dry particulate contaminants may be present.



DESCRIPTION:

DEFENDER™ Microporous Coveralls with Attached Hood, Zipper Front, Elastic at Hood, Wrists & Ankles

See attached Physical Properties

CERTIFICATIONS & RATINGS:

Made with FDA Approved Materials for Food Contact Applications. (U.S. Code of Federal Regulations, 21CFR, Parts 170-199)

ANSI/ISEA 101 Compliant Sizing

APPLICATIONS:



AGRICULTURE



PAINTING



FOOD PROCESSING



LABORATORIES

ORDERING:

Unit of Sale: One Case
Packaging: 5 EA/Polybag
Case Pack: 25 EA/Case
COO: China
Available Sizes: M-5XL

BARCODES:

ITEM	ITEM UPC	CASE UPC
CPHM	796326343111	50796326343116
CPHL	796326343128	50796326343123
CPHXL	796326343135	50796326343130
CPHXXL	796326343142	50796326343147
CPHXXXL	796326343159	50796326343154
CPHXXXXL	796326343166	50796326343161
CPHXXXXXL	796326343180	50796326343185

CARE:

Dispose after each use.

Case Weight (lbs)

M	L	XL	2XL
10	12	12	13
3XL	4XL	5XL	
13	14	15	

Corporate Headquarters:

4025 Viscount Avenue
 Memphis, TN 38118
 Phone 800.458.8763
 Fax 901.458.3343

CORE SAFETY PROTECTION
www.cordovasafety.com

West Coast Office:

433 Cheryl Lane (Dock Door 14)
 City of Industry, CA 91789
 Phone 909.590.2679
 Fax 909.590.3130

PHYSICAL PROPERTIES

DEFENDER™ Coveralls

TEST DATA

PHYSICAL PROPERTY	TEST METHODS	UNITS	RESULTS
Fabric Weight	IST130.1	gsm	59.85/1.77 oz
MD Tensile (Grab)	IST110.1	lbs/in	27.6
CD Tensile (Grab)	IST110.1	lbs/in	18.5
MD Elongation	IST110.1	%	71.9
CD Elongation	IST110.1	%	79.5
MD Tear Strength (Trapezoid)	IST100.2	lbs/in	7.5
CD Tear Strength (Trapezoid)	IST100.2	lbs/in	11.3
Bursting Strength (Mullen Burst)	IST 30.1	psi	32.0
Hydrostatic Head	IST 80.6-01 (Testex)	cm	191.3
Static Decay(MD) (50%RH)+	IST 40.2	sec	Pass
Resistance to Blood Penetration	ASTM 1670	Procedure B	Pass

*These physical properties represent typical values of the non-woven fabric. These values should not be considered as a specification or certificate of material and/or specification value. Testing was performed on base material.

Corporate Headquarters:

4025 Viscount Avenue
Memphis, TN 38118
Phone 800.458.8763
Fax 901.458.3343

CORE SAFETY PROTECTION
www.cordovasafety.com

West Coast Office:

433 Cheryl Lane (Dock Door 14)
City of Industry, CA 91789
Phone 909.590.2679
Fax 909.590.3130

